# **Technical datasheet**

# Alloy 400 / W-Nr. 2.4360/2.4361

A nickel-copper alloy with good strength and excellent corrosion resistance used for marine engineering and chemical processing equipment.

# Available products

Product formSize range fromSize range toSheet/plate0.5 mm thickness40.0 mm thicknessBar6.0 mm diameter200.0 mm diameter

Tube/pipe 10.0 mm outside diameter 219.1 mm outside diameter

#### Chemical composition (%)

Ni	Cu	Fe	Mn	S	Si	С		
63.0 min	28.0-34.0	1.0-2.5	2.0 max	0.024	0.5 max	0.3 max		

#### **Major specifications**

ASTM B127, B163, B164, B165, B366, B564, B829 UNS N04400 NACE MR-0175, VdTŰV 263 UNS N04700 DIN 17750, 17752

### **Physical properties**

Density 8.80 g/cm<sup>3</sup> Melting range 1300-1350°C

#### **Mechanical properties** – typical room temperature properties

Yield strength 240 MPa Tensile strength 550 MPa Elongation 40 %

## **Key attributes**

Alloy 400 has good strength and toughness over a wide temperature range. At sub-zero temperatures the strength increases with only a slight negative effect on the ductility and impact resistance. It has excellent corrosion resistance in reducing media and is resistant to chloride induced stress corrosion cracking and pitting in fresh and industrial process waters. In sea water Alloy 400 exhibits very low corrosion rates and has excellent resistance to neutral and alkaline salts. It has excellent resistance to hydrofluoric acid and resists most sulphuric and hydrochloric acids under reducing conditions.

Alloy 400 is highly fabricable and is readily formed by either hot or cold working processes. It is machinable and can be welded by conventional processes and procedures. Please contact us for further details on forming, fabrication and welding consumables.

### **Applications**

Marine engineering valves, pump and propeller shafts Heat exchangers in the chemical processing industry Brine heaters and evaporators Fittings and fasteners Electrical and electronic applications Sulphuric and hydrofluoric acid systems



