

Technical datasheet

Alloy 42 / W-Nr. 1.3917

A binary nickel-iron alloy containing 42% nickel with a largely constant coefficient of thermal expansion making it ideal for glass-to-metal sealing systems, thermostat components and in semiconductors.

Available products

Product form

Sheet/plate
Bar

Size range from

0.25 mm thickness
2.50 mm diameter

Size range to

38.10 mm thickness
31.75 mm diameter

Chemical composition (%)

Ni	Fe	Co	Mn	Si	Cr	Al	C
42	Balance	1.0 max	0.8 max	0.30 max	0.25 max	0.15 max	0.05 max

Major specifications

ASTM F29, F30, B753
SEW 385

UNS K94100

Physical properties

Density	8.11 g/cm ³	Coefficient of thermal expansion (20-100°C)
Melting temperature	1435°C	5.3 µm/m•C

Mechanical properties – typical room temperature properties

Yield strength	250 MPa
Tensile strength	490 MPa
Elongation	%

Key attributes

Alloy 42 has a low, relatively constant coefficient of thermal expansion from room temperature to 300°C. In applications where maximum dimensional stability is required Alloy 42 should be used in the annealed condition. It is used widely in glass-to-metal sealing systems as its coefficient of expansion closely matches that of 98% alumina borosilicate glasses.

Alloy 42 is readily formed by both hot and cold forming and can be machined. Workability characteristics are similar to those of austenitic stainless steels. Alloy 42 can be welded by most standard techniques. Please contact us for further details on forming and fabrication.

Applications

Tooling for aerospace composites
Glass-to-metal and ceramic-to-metal sealing applications
Sealed unit automotive head lamps
Vacuum devices
Bi-metallic components and thermostatic applications
Electronic circuit lead frames

Do you require further information or a quotation?

Please contact us...

info@bibusmetals.com

www.bibusmetals.com

BIBUS METALS
SUPPORTING YOUR SUCCESS